

# FARCO TILE F10

## Polymer Modified, Cementitious Grout for Outdoor and Indoor

### Product Description

FARCOTILE F10 is a ready for use tile grout consist of cement, mineral powders, polymer and Adhesion promoters for grouting floor and wall tiles

#### ● Uses

FARCOTILE F10 is suitable for grouting every kind of stone, on wall or floor. For indoor or out door applications such as kitchens, bathrooms, swimming pools

#### ● Advantages

- Easy to apply, Non slump and High adhesion
- Very low water absorption
- Different colors
- Frost resistant

#### ● Direction for Use

##### Substrate Preparation

- For an optimal of the tiles, the joints must be carefully cleaned and free from adhesive and dampened with wet sponge.

##### Mixing and Application

- Add F10 powder to cool and clean water and stir approx. 1 minute by an electric stirrer, to a smooth and homogenous mixture. The mixture should be left about 5 minutes to settle and slightly stirred again.
- The recommended air and substrate temperature is between 10 to 35°C.

Suitable for grouting joints with 3 to 15mm width

- Spread the grout on to the joints, using a rubber spatula or a grouting trowel diagonally in relation to the direction of joints in such way, that joints should be completely filled. Apply the mortar within 1 hour at 25°C, Remove excess material immediately when F10 is still plastic.
- After the grout is dry but not completely hardened, clean the surface with wet sponge following with dry cloth.

#### ● Technical Information

Base	Cement
Color	according to the request
Appearance	Powder
PH	Alkali
Specific Gravity (Powder)	1.35±0.02kg/lit
Specific Gravity (Paste)	1.9±0.02kg/lit

#### ● Packaging

FARCOTILE F10 is supplied in 5kg plastic bags.

#### ● Storage and shelf life

6 month when stored at temperatures between 5 to 35°C in dry place and unopened original package.

#### ● Technical Service

The SHIMISAKHTEMAN Technical Service Department is available to assist you in the correct use of our products in the field.



242 Bldg., Mirdamad Blvd., After Naft St., Tehran. Iran

Tel: +98 21 (22263100 , 22263099 , 22259736) Fax:+98 21 22260586



Shimi Sakhteman

+98 21 27427