



## Cement Based Self leveling Tile Grout for Outdoor and Indoor

### Product Description

- FARCOTILE F14 is a ready for use tile grout consists of cement, mineral powders, shrinkage compensating and adhesion promoters materials.
- F14 is suitable for making grouts with flowable consistency for wide (3 to 15 mm) floor joints and plastic consistency for walls.

### Application

For grouting tile, Mosaic, natural or artificial stone joints in bathrooms, kitchens and residential or administrative areas.

### Advantages

- Easy application, Non shrink, Different colors
- Self leveling
- Frost resistant
- Easy to clean therefore suitable for bricks and decorative stones.

### Direction for Use

#### Substrate Preparation

- For a grouting of the tiles, the joints must be carefully cleaned and free from adhesive and dampened with wet sponge.

#### Mixing and Application

- Add F14 grouting to a cool and clean water and stir approx. 1 minute by an electric stirrer to a smooth and homogenous mixture. The mixture should be left about 5 minutes to settle and then slightly stirred

again.

The recommended air and substrate temperature is between 10 to 35°C

- Suitable for grouting joints with 3 to 15mm width
- Spread the grout on to the joints, using a rubber spatula or a grouting trowel diagonally in relation to the direction of joints in such way, that joints should be completely filled. Apply the mortar within 1 hour at 25°C; remove excess material immediately when F14 is still plastic.
- After the grout is dry but not completely hardened, clean the surface with wet sponge following with dry cloth.

### Packaging

FARCO TILE F14 is supplied in 20kg bags.

### Storage and shelf life

6 month when stored at temperatures between 5 to 35°C in dry place and unopened original package.

### Safety and Handling Precautions

F14 contains cement, while mixing and application use mask and wear gloves wash skin with clean water.

### Technical Service

The SHIMISAKHTEMAN Technical Service Department is available to assist you in the correct use of our products in the field.



242 Bldg., Mirdamad Blvd., After Naft St., Tehran. Iran

Tel: +98 21 (22263100 , 22263099 , 22259736) Fax:+98 21 22260586

Shimi Sakhteman



+98 21 27427