



FARCO PLAST PS10

High Range Water reducing with an Extended Slump Retention Admixture Based on Polycarboxylate

Product Description

FARCOPLASTP PS10 is a slump keeping 3rd generation polycarboxylate superplasticizer designed for high slump retention concrete.

PS10 is recommended for concretes which slumps needs to be maintained from 1 to 6 hours

● Mechanism of Action

The two most important mechanism attributed to dispersion in polycarboxylate systems are linked to polymer adsorption and steric hindrance caused by the thickness of the adsorbed polymer layer on to the cement particle and repulsion through induced electrical electrostatic charge.

● Concrete Workability

The fluidified concrete remains workable for approximately 1-6 hours at 20°C (concrete temperature). Duration of workability depends not only on the temperature, but also on the type and brand of cement, the nature of the aggregates, the method of mixing, the method of transportation and the amount of added admixture.

● Applications

- Tremie concrete
- Hot weather concreting
- Suitable for cements with high slump losses
- Concrete containing fly ash or silica fume

- Blast furnace slag cement concrete
- Pumping concrete

● Advantages

- Provides a cohesive non segregating concrete mixture
- Concretes with slump retention properties of 1 to 6 hours Improves impermeability against sulfate, chloride and water due to reduced water content
- Improves abrasion and frost resistance by decreasing W/CM
- PS10 is specially suitable for producing high workability concrete that has excellent workability retention, in this application, extension in setting time and little loss in early age compressive strength are observed.
- Reduced dosage range in comparison with conventional polycarboxylates.

● Standard Compliance

- FARCOPLAST PS10 complies with
- ASTM C 494 -Type G
 - ISIRI 2930 -Table 11 , 13
 - EN 934-2 -Table 11.1 - 11.2

● General Properties

Chemical Composition	Modified polycarboxylate ether
Ionic nature	Anionic
Appearance	Light Brown yellow
Specific Gravity	Typically 1.09±0.02 at 20°C
Chlorides (PPM)	500 max

FARCO PLAST PS10

● Dosage

· PS10 is normally dosed at a rate of 0.4-1.4% by weight of cementitious materials.

· Dosage recommendations depend on the characteristics of the mix design.

Field testing is recommended to determine the optimum dosage and effect on both plastic and hardened concrete properties such as : workability and workability retention, setting time, early and ultimate strength.

● Method of use

· FARCOPLAST PS10 is supplied ready for use and is completely miscible in water.

· It can be added in to the mixer at the same time as the mixing water.

· It should not be added directly to the cement or dry materials.

· FARCOPLAST PS10 may be added at the end of mixing process by dispensing equipment or it may also be added to the concrete in a drum of ready mix truck, it should be mixed at least 1 minute per m³ of concrete at high speed.

● Compatibility

With cements

FARCOPLAST PS10 is suitable for use with cement

replacement materials e.g. Fly ash, silica fume and blast furnace slag cement concrete.

With other Admixtures

FARCOPLAST PS10 should not be premixed or used with other admixtures unless receive the approval from manufacturer. We would recommend that SHIMISAKHTEMAN be consulted in such circumstances.

● Packaging

FARCOPLAST PS10 is supplied in 20kg gallons, 220kg drums and 1100 kg IBC tanks.

● Storage

FARCOPLAST PS10 Storage is recommended to keep within the range of 5°C to 40°C. If product has frozen, thaw and agitate until completely reconstituted Keep out of direct sunlight.

● Shelf life

12 month when PS10 is kept under the recommended conditions and stored in unopened and undamaged original sealed containers.

● Safety and Handling Precautions

PS10 is a product classified as harmless, but in the line with general chemical handling precautions to avoid contact with skin or eyes, protective gloves and goggles should be worn.

● Technical Service

The SHIMISAKHTEMAN Technical Service Department is available to assist you in the concrete problems in the field and correct use of our products.



242 Bldg., Mirdamad Blvd., After Naft St., Tehran. Iran

Tel: +98 21 (22263100 , 22263099 , 22259736) Fax:+98 21 22260586

Shimi Sakhteman



+98 21 27427